



CONROCK

Serving The Building Industry
For Over Fifty Years

KILN-DRIED ROOFING AGGREGATES

KILN-DRIED ROOFING AGGREGATE produced by ConRock is carefully processed to assure the user of an aggregate that is:

DRY - to facilitate in providing a secure bond and to eliminate the formation of blisters in the asphalt.

CLEAN - to eliminate foreign particles and excessive fines so that it will become tightly bonded to the asphalt.

OPAQUE - to prevent passage of harmful ultra violet rays from sun.

ACCURATELY GRADED - to provide MAXIMUM COVERAGE!



SPCR 5/8 x 1/4
Crushed Rock. Designed to meet A.S.T.M. Specification D-1863-64. 400 to 500 lbs. per 100 Square Feet.

SPG 3/8 x 4
Natural Gravel. Designed to meet Uniform Building Code, F.H.A. and L.A. City Schools Specifications. 350 to 400 lbs. per 100 Square Feet



SPCR 3/8
Crushed Rock
300 to 350 lbs. per 100 Square Feet.

SPCR 3/8 - 1/4 Blend
Crushed Rock
250 to 350 lbs. per 100 Square Feet.



SPCR 1/4
Crushed Rock
200 to 250 lbs. per 100 Square Feet.

SPCR 9 x 35
Crushed Granule for paste type roofing.
100 to 125 lbs. per 100 Square Feet.



Materials are available for delivery in Bulk Loads, Sacks (80# paper sacks) or Pneumatic Tank Trucks — to meet job requirements regardless of size.

MEMBRANE ROOFING
Roof Aggregates

CONSOLIDATED ROCK PRODUCTS CO.

Specialty Products Division
15700 East Arrow Highway, Irwindale, California • (213) 962-7071

Los Angeles Area (213) 233-3111 • San Diego Area (714) 298-0551 • Orange County Area (714) 538-1127
Ventura-Santa Barbara Area (805) 647-1121 • Antelope Valley Area (805) 942-9571

AIA FILE NO. 12-A-7

Suggested

AGGREGATE SPECIFICATIONS FOR BUILT-UP ROOFING

CRUSHED ROCK — The roofing aggregate shall be durable, hard, opaque, less than 0.5% by weight moisture, free of deleterious materials, crushed rock of natural gray color. It shall be screened to meet the following U.S. Standard sieve limitations:

ConRock SPCR 5/8 x 1/4 (400 to 500 lbs. per 100 Square Feet)

Sieve Size	5/8"	3/8"	#4	#8
% Passing	100	40-70	0-10	0-5

This material is designed to meet A.S.T.M. Specification D-1863-64

ConRock SPCR 3/8 (300 to 350 lbs. per 100 Square Feet)

Sieve Size	1/2"	3/8"	#3	#4	#8	#16
% Passing	100	90-100	70-90	30-50	2-5	0-2

ConRock SPCR 1/4 (200 to 250 lbs. per 100 Square Feet)

Sieve Size	1/2"	3/8"	#3	#4	#8	#16	#30
% Passing	—	100	90-100	80-90	20-40	0-10	0-3

ConRock SPCR 3/8 - 1/4 Blend (250 to 300 lbs. per 100 Square Feet)

Sieve Size	1/2"	3/8"	#3	#4	#8	#16	#30
% Passing	100	95-100	90-100	65-90	10-25	0-5	0-1

ConRock SPCR 9 x 35 (100 to 125 lbs. per 100 Square Feet)

Sieve Size	#8	#12	#16	#20	#30	#50
% Passing	100	95-100	45-75	20-40	0-5	0-1

GRAVEL — The roofing aggregate shall be durable, hard, opaque, less than 0.5% by weight moisture, free of deleterious materials, washed bank or river gravel of natural gray color. It shall be screened to meet the following U.S. Standard sieve limitations:

ConRock SPG 3/8 x #4 (350 to 400 lbs. per 100 Square Feet)

Sieve Size	1/2"	3/8"	#3	#4	#8
% Passing	100	95-100	30-50	0-10	0-2

This material is designed to meet Uniform Building Code Specifications.



CONROCK KILN-DRIED ROOFING AGGREGATE

Covering Roofs Throughout The West

CONSOLIDATED ROCK PRODUCTS CO.

General Offices Mailing Address:

P.O. Box 2950 Terminal Annex, Los Angeles, California 90054

Producers Of:

SAND • GRAVEL • CRUSHED ROCK • READY MIXED CONCRETE • LIGHTWEIGHT CONCRETE • KILN-DRIED ROOFING ROCK • GRANITE POULTRY GRITS • BLASTING SAND

